



Product name		Product group	Production location
Morvan		D5	Hedikhuizen
A mix of different kinds of clay forms the basis for this facing brick. This special mix of clays is ideally suited for the manufacturing of hand form bricks. By using specific sand types for surface covering, the desired colour is achieved.			
Colour			
No description			
Format			
Moulding method		Hand form	
WF: 207 x 99 x 50 mm DF: 214 x 101 x 65 mm LF40: 245 x 90 x 40 mm : 245 x 90 x 40 mm		Between batches the average size and color may slightly differ.	
Essential Characteristics - EN771-1			
 0620-CPR-97880			
Dimensional tolerances	T2		
Range	R1		
Active Soluble Salts	S2		
Mean Compressive strength	$\geq 20 \text{ N/mm}^2$	Tested to the bed face	
Normalized Compressive strength	$\geq 20 \text{ N/mm}^2$	Tested to the bed face	
Dimensional stability	NPD		
Bond Strength general	0,15 N/mm ²		
Bond Strength thin layer	0,30 N/mm ²		
Reaction to fire	A1	Category	
Water absorption	$\leq 10\% \text{ m/md}$		
Water vapour permeability	50/100		
Net dry density	2050 kg/m ³ (D1)		
Gross dry density	1880 kg/m ³ (D1)		
Thermal conductivity Lambda 50/50	$\leq 0,60 \text{ W/m.K}$		
Durability against freeze thaw	F2		
Dangerous substances	NL-BSB	According to Annex ZA 3	
Other Characteristics			
Initial rate of water absorption - Non-coated Bricks	1,5 - 4,0 kg/m ² .min (IW3)	Value according EN771-1:2011 - 5.3.8	
Initial rate of water absorption - Coated bricks	0,5 - 1,5 kg/m ² .min (IW2)	Value according EN771-1:2011 - 5.3.8	
Freeze/thaw resistance	NPD	B 27-009	
Thermal conductivity Lambda 90/90	NPD		
Thermal conductivity Lambda Ui	NPD		
Thermal conductivity Lambda Ue	NPD		
			
Storage & handling		Cutting	
<ul style="list-style-type: none"> - Store packs on a clean surface and cover them - Process from multiple packs at the same time - Follow the Vandersanden processing guidelines 		Cutting with power tools may generate dust. This dust may contain silica or quartz particulate which may constitute a hazard. Persons undertaking work of this nature are advised to wear dust masks (FFP3).	
<small>*All our Coated bricks are only coated on the facing sides. Coated products are specially labeled and recognisable with a "C" logo on the top left-hand side of the packaging. Always check if using coated or non-coated bricks. Match the mortar to the specified initial water absorption.</small>			

Product name	Product group	Production location
Morvan	S8	Spijk
A mix of different kinds of clay forms the basis for this facing brick. This special mix of clays is ideally suited for the manufacturing of hand form bricks. By using specific sand types for surface covering, the desired colour is achieved.		
Colour		
No description		
Format		
Moulding method	Hand form	
WF: 208 x 98 x 51 mm	Between batches the average size and color may slightly differ.	
Essential Characteristics - EN771-1		
 0620-CPR-76485		
Dimensional tolerances	T2	
Range	R1	
Active Soluble Salts	S2	
Mean Compressive strength	$\geq 17,5 \text{ N/mm}^2$	Tested to the bed face
Normalized Compressive strength	$\geq 17,5 \text{ N/mm}^2$	Tested to the bed face
Dimensional stability	NPD	
Bond Strength general	$0,15 \text{ N/mm}^2$	
Bond Strength thin layer	$0,30 \text{ N/mm}^2$	
Reaction to fire	A1	Category
Water absorption	$\leq 8\% \text{ m/md}$	
Water vapour permeability	50/100	
Net dry density	$2100 \text{ kg/m}^3 \text{ (D2)}$	
Gross dry density	$1880 \text{ kg/m}^3 \text{ (D1)}$	
Thermal conductivity Lambda 50/50	$\leq 0,62 \text{ W/m.K}$	
Durability against freeze thaw	F2	
Dangerous substances	NL-BSB	According to Annex ZA 3
Other Characteristics		
Initial rate of water absorption - Non-coated Bricks	$0,5 - 1,5 \text{ kg/m}^2 \cdot \text{min (IW2)}$	Value according EN771-1:2011 - 5.3.8
Initial rate of water absorption - Coated bricks	NPD	Value according EN771-1:2011 - 5.3.8
Freeze/thaw resistance	NPD	B 27-009
Thermal conductivity Lambda 90/90	NPD	
Thermal conductivity Lambda Ui	NPD	
Thermal conductivity Lambda Ue	NPD	
		
Storage & handling		Cutting
<ul style="list-style-type: none"> - Store packs on a clean surface and cover them - Process from multiple packs at the same time - Follow the Vandersanden processing guidelines 		Cutting with power tools may generate dust. This dust may contain silica or quartz particulate which may constitute a hazard. Persons undertaking work of this nature are advised to wear dust masks (FFP3).
<small>*All our Coated bricks are only coated on the facing sides. Coated products are specially labeled and recognisable with a "C" logo on the top left-hand side of the packaging. Always check if using coated or non-coated bricks. Match the mortar to the specified initial water absorption.</small>		

Product name		Product group	Production location
Morvan		S4	Spijk
A mix of different kinds of clay forms the basis for this facing brick. This special mix of clays is ideally suited for the manufacturing of hand form bricks. By using specific sand types for surface covering, the desired colour is achieved.			
Colour			
No description			
Format			
Moulding method		Hand form	
DF: 208 x 101 x 65 mm		Between batches the average size and color may slightly differ.	
Essential Characteristics - EN771-1			
 0620-CPR-76485			
Dimensional tolerances	T2		
Range	R1		
Active Soluble Salts	S2		
Mean Compressive strength	$\geq 30 \text{ N/mm}^2$	Tested to the bed face	
Normalized Compressive strength	$\geq 30 \text{ N/mm}^2$	Tested to the bed face	
Dimensional stability	NPD		
Bond Strength general	$0,15 \text{ N/mm}^2$		
Bond Strength thin layer	$0,30 \text{ N/mm}^2$		
Reaction to fire	A1	Category	
Water absorption	$\leq 7\% \text{ m/md}$		
Water vapour permeability	50/100		
Net dry density	$2000 \text{ kg/m}^3 \text{ (D1)}$		
Gross dry density	$1900 \text{ kg/m}^3 \text{ (D1)}$		
Thermal conductivity Lambda 50/50	$\leq 0,53 \text{ W/m.K}$		
Durability against freeze thaw	F2		
Dangerous substances	NL-BSB	According to Annex ZA 3	
Other Characteristics			
Initial rate of water absorption - Non-coated Bricks	$0,5 - 1,5 \text{ kg/m}^2 \cdot \text{min (IW2)}$	Value according EN771-1:2011 - 5.3.8	
Initial rate of water absorption - Coated bricks	NPD	Value according EN771-1:2011 - 5.3.8	
Freeze/thaw resistance	NPD	B 27-009	
Thermal conductivity Lambda 90/90	NPD		
Thermal conductivity Lambda Ui	NPD		
Thermal conductivity Lambda Ue	NPD		
			
Storage & handling		Cutting	
<ul style="list-style-type: none"> - Store packs on a clean surface and cover them - Process from multiple packs at the same time - Follow the Vandersanden processing guidelines 		Cutting with power tools may generate dust. This dust may contain silica or quartz particulate which may constitute a hazard. Persons undertaking work of this nature are advised to wear dust masks (FFP3).	
<small>*All our Coated bricks are only coated on the facing sides. Coated products are specially labeled and recognisable with a "C" logo on the top left-hand side of the packaging. Always check if using coated or non-coated bricks. Match the mortar to the specified initial water absorption.</small>			